

Distribution of the local density of states, reflection coefficient and Wigner delay time in absorbing ergodic systems at the point of chiral symmetry

Yan V. Fyodorov^{1,*} and Alexander Ossipov²

¹*Department of Mathematical Sciences, Brunel University, Uxbridge UB83PH, United Kingdom and*

²*Max-Planck-Institut für Strömungsforschung, 37073 Göttingen, Germany*

(Dated: February 2, 2008)

Employing the chiral Unitary Ensemble of random matrices we calculate the probability distribution of the local density of states for zero-dimensional ("quantum chaotic") two-sublattice systems at the point of chiral symmetry $E = 0$ and in the presence of uniform absorption. The obtained result can be used to find the distributions of the reflection coefficient and of the Wigner time delay for such systems.

PACS numbers: 05.45.Mt, 11.30.Rd

Spectral and transport properties of quantum systems with chiral symmetries attracted a considerable attention recently [1, 2, 3, 4, 5, 6, 7, 8]. The systems of the discussed type are characterized by random Hamiltonians of the form:

$$\mathcal{H}_{ch} = \begin{pmatrix} 0 & \hat{H} \\ \hat{H}^\dagger & 0 \end{pmatrix} \quad (1)$$

serving to describe various physical situations, e.g. lattice systems with bond disorder of pure nearest-neighbour hopping type [1, 2, 3, 4], random magnetic flux models appearing in the context of the Quantum Hall effect [5], as well as lattice QCD models [6]. Many other interesting examples can be found in the cited literature.

Replacing the block $\hat{H}$ in Eq.(1) with random rectangular matrices of the size $N_A \times N_B$ with independent, Gaussian-distributed complex entries we arrive at the object known as the chiral Gaussian Unitary Ensemble (chGUE) [9]. In the language of the two-sublattice disordered lattice system this model is known to correspond to the so-called universal ergodic (or "zero-dimensional", or "quantum dot") limit adequate if we are interested in energies smaller than the so-called Thouless energy E_c . The latter requirement means that the time to diffusively propagate through the system is much shorter than $\hbar/\Delta$, with Δ standing for the mean level spacing in the relevant energy range. Spectral statistics of chGUE matrices is well-studied by various methods and many explicit results are available [10, 11, 12, 13, 14, 15].

One of the most striking features of the spectra of chiral systems is a specific behaviour of the spectral characteristics at zero energy. In zero-dimensional chiral systems this specific behaviour is manifested, in particular, via vanishing of the mean eigenvalue density $\rho_{av}(E)$ at the middle of the band, $E = 0$, as long as $N_A = N_B$. For $N_A \neq N_B$ there exist exactly $|N_A - N_B|$ zero eigenvalues. All nonzero eigenvalues for chiral models appear in pairs $\pm\lambda_n$, with the corresponding eigenvectors being $|w_n^\pm\rangle = \begin{pmatrix} \mathbf{u}_n \\ \pm\mathbf{v}_n \end{pmatrix}$. Here $\mathbf{u}_n$ and $\mathbf{v}_n$ are eigenvectors of the Hermitian matrices $\hat{H}\hat{H}^\dagger$ and $\hat{H}^\dagger\hat{H}$, of the size $N_A \times N_A$

and $N_B \times N_B$, respectively. To ensure the orthonormality of the eigenvectors $\langle w_m^\pm | w_n^\pm \rangle = \delta_{mn}$ we choose the normalisation $\mathbf{v}_n^\dagger \mathbf{v}_n = \mathbf{u}_n^\dagger \mathbf{u}_n = 1/\sqrt{2}$.

We first assume, for simplicity, that the number of lattice sites in the two sublattices are equal: $N_A = N_B = N$ and define in a usual way the exact local density of states (LDOS) at a site $j_A = 1, 2, \dots, N$ of the sublattice A via the relation:

$$\rho_{j_A}(E_\eta) = \frac{1}{\pi} \text{Im} \langle j_A | \frac{1}{E_\eta - \mathcal{H}} | j_A \rangle \quad (2)$$

$$= \frac{2}{\pi} \text{Im} \sum_{n=1}^N |u_n(j)|^2 \frac{E_\eta}{E_\eta^2 - \lambda_n^2} \quad (3)$$

where $u_n(j)$ stands for j -th component of the eigenvector $\mathbf{u}_n$. Here we assume that the energy $E_\eta = E - i\eta$ is complex, the parameter $\eta > 0$ standing for the level broadening due to an absorption, i.e. uniform-in-space losses of the flux of particles in the sample. In particular, for the energy E chosen precisely in the center of the spectrum ("the point of chiral symmetry") the LDOS is given by the most simple expression:

$$\rho_{j,A}(\eta) = \frac{2}{\pi} \sum_{n=1}^N |u_n(j)|^2 \frac{\eta}{\eta^2 + \lambda_n^2}. \quad (4)$$

For the lattice sites of the sublattice B the LDOS is given by the same formula, with $\mathbf{u}_n(j)$ replaced by $\mathbf{v}_n(j)$.

The above expression is a very convenient starting point for calculating the distribution function of the local DOS at the spectrum center. In doing this we employ the method suggested for GUE without chiral structure in [16]. Namely, we consider the generating function (the Laplace transform of the probability density) $P(t) = \langle e^{-t\rho_{j,A}} \rangle_{chGUE}$ where the angular brackets stand for the ensemble averaging. Using that the eigenvalues λ_n are statistically independent of the eigenvectors $\mathbf{u}_n, \mathbf{v}_n$, and the components of the latter vectors behave in the large N limit like independent complex Gaussian variables with zero mean and variances

$\langle |u_n(j)|^2 \rangle_{chGUE} = \frac{1}{2N}$ one can first perform the ensemble average over eigenvectors. After simple manipulations one arrives at the following representation for the generating function:

$$P(t) = \left\langle \frac{\det(\eta^2 + \hat{H} \hat{H}^\dagger)}{\det(\tilde{\eta}^2 + \hat{H} \hat{H}^\dagger)} \right\rangle_H \quad (5)$$

where we denoted $\tilde{\eta} = \sqrt{\eta^2 + \eta t / (\pi N)}$. In this way the problem of calculating the generating function in question is reduced to evaluating the ensemble average of the ratio of characteristic polynomials of the random matrices $\hat{H} \hat{H}^\dagger$. The latter object (and its generalisations) were intensively studied in the literature recently, see [13, 15], and the result is readily available:

$$P(t) = \frac{\pi}{2} \left[\epsilon I_1(\epsilon) K_0 \left(\sqrt{\epsilon(\epsilon + 2t/\pi)} \right) + \left(\sqrt{\epsilon(\epsilon + 2t/\pi)} \right) K_1 \left(\sqrt{\epsilon(\epsilon + 2t/\pi)} \right) I_0(\epsilon) \right] \quad (6)$$

where we denoted $\epsilon = 2N\eta$ and considered this parameter to be finite when performing the large- N limit. Here $I_n(z), K_n(z)$ stand for the modified Bessel and Macdonald functions of the order n , respectively. The distribution function $\mathcal{P}(\rho_A)$ of the LDOS can be found by inverting the Laplace transform Eq.(6) with respect to t and is given by:

$$\mathcal{P}(\rho_A) = \frac{\epsilon}{2\rho_A} e^{-\frac{\epsilon}{2}(\pi\rho_A + 1/\pi\rho_A)} \left[I_1(\epsilon) + \frac{1}{\pi\rho_A} I_0(\epsilon) \right] \quad (7)$$

Having the LDOS distribution at our disposal, we can further utilise it for obtaining distributions of various physical quantities of much interest describing scattering of a quantum particle from the two-sublattice disordered sample. In doing this we follow the method suggested recently by the first author in [17]. Consider a particle injected into the site j_A of the sublattice A through a one-channel infinite lead perfectly coupled to the system. The scattering of such a particle from our absorptive sample is described by the scattering matrix S_{jA} expressed in terms of the matrix elements of the resolvent associated with the chiral Hamiltonian $\mathcal{H}$:

$$S_{jA}(E_\eta) = \frac{1 - iG}{1 + iG} \quad , \quad G = \pi \langle j_A | \frac{1}{E_\eta - \mathcal{H}} | j_A \rangle. \quad (8)$$

In this way the problem of investigating statistics of the scattering matrix amounts to that of the diagonal entry G of the resolvent. For an arbitrary energy E the variable G is a complex quantity and one has therefore to know the joint probability density of its real and imaginary parts. However, at the point $E = 0$ of chiral symmetry G turns out to be purely imaginary and therefore just proportional to the LDOS, Eq.(4), whose distribution $\mathcal{P}(\rho_A)$ was calculated above, Eq.(7). As a result we can calculate the distribution of the reflection coefficient




FIG. 1: Numerical (symbols) and analytical (solid lines) results for the LDOS distribution of the sublattice A for $\epsilon = 1$, $N_B = 300$ and $N_A = 300 - l$, $l = 0, 1, 2, 3$.

$R_{jA}(\eta) = |S_{jA}(\eta)|^2$. Below we present the distribution of a related object $\tau = 1 - R_{jA} = 4\pi\rho_{jA}/(1 + \pi\rho_{jA})^2$ which, following [17], we suggest to call the "probability of no return" (PNR). This quantity has meaning of the quantum-mechanical probability for a particle entering the system via a given channel never exit back to the same channel. It is well-defined for a given realization of disorder and will therefore show sample-to-sample fluctuations. Let us stress that in the case $\eta = 0$ of no internal dissipation S -matrix is unitary for any energy and PNR is vanishing identically. For a system with absorption the unitarity is violated, giving rise to a nontrivial statistics of τ :

$$\mathcal{P}(\tau) = \frac{\epsilon}{\tau\sqrt{1-\tau}} e^{-\epsilon(\frac{2}{\tau}-1)} \left[I_1(\epsilon) + \left(\frac{2}{\tau} - 1 \right) I_0(\epsilon) \right] \quad (9)$$

The above distribution can be further utilized for finding statistics of such interesting characteristic of quantum scattering as the so-called Wigner delay time $\tau_W = -i\partial S/\partial E$ intensively studied in recent years, see [18],[19],[20],[21] and references therein. This can be done again following [17], see also [21]. Indeed, remembering that nonzero values of τ arise solely due to an absorption, one can relate for small absorption the PNR value to the Wigner delay time by $\tau \simeq 2\epsilon\tau_W$ [19]. Taking the corresponding limit in the distribution (9) we arrive at the distribution of the scaled variable $\tilde{\tau}_W = \tau_W/2N$:

$$\mathcal{P}(\tilde{\tau}_W) = \frac{1}{\tilde{\tau}_W^2} e^{-\frac{1}{\tilde{\tau}_W}} \quad (10)$$

The expression Eq.(10) should be compared with the corresponding formula for the one perfect channel attached to an ergodic system modelled by GUE, i.e. without the chiral symmetry [18]: $\mathcal{P}(\tilde{\tau}_W) = \frac{1}{\tilde{\tau}_W^3} e^{-\frac{1}{\tilde{\tau}_W}}$. The




FIG. 2: Numerical (symbols) and analytical (solid lines) results for the LDOS distribution of the sublattice B for $\epsilon = 1$, $N_B = 300$ and $N_A = 300 - l$, $l = 0, 1, 2, 3$.

crossover between the two types of behavior is expected to happen in the present model with increasing energy parameter E from zero to values much exceeding the mean level spacing. Investigating this interesting question requires however much more elaborate methods and is left for future research.

Let us now briefly discuss generalization of our results to the case of non-equivalent sublattices $N_B > N_A$. Note that in this case exactly $N_B - N_A = l$ zero modes are supported by the sublattice B , whereas only modes with nonzero eigenvalues give contribution to the LDOS for the sublattice A . Assuming that $l \ll N_A, N_B$ one finds that LDOS distribution for the sites belonging to the sublattice A is given by formula generalizing Eq.(7):

$$\mathcal{P}_l(\rho_A) = \frac{\epsilon}{2\pi^l \rho_A^{l+1}} e^{-\frac{\epsilon}{2}(\pi \rho_A + 1/\pi \rho_A)} \left[I_{l+1}(\epsilon) + \frac{1}{\pi \rho_A} I_l(\epsilon) \right] \quad (11)$$

whereas the LDOS distribution $\mathcal{P}_l(\rho_B)$ for sites belonging to the sublattice B is obtained from the above formula by replacing l with $-l$. In Fig. (1) and Fig. (2) we compare this prediction with the results of direct numerical simulations of the random matrix Hamiltonian Eq.(1), for sublattices A and B correspondingly. It is instructive to compare the behavior of the mean LDOS for the two sublattices in the limit $\epsilon \rightarrow 0$:

$$\langle \rho_A \rangle = \frac{\epsilon}{2} [I_{l+1}(\epsilon) K_{l-1}(\epsilon) + I_l(\epsilon) K_l(\epsilon)] \rightarrow \frac{\epsilon}{4l} \quad (12)$$

$$\langle \rho_B \rangle = \frac{\epsilon}{2} [I_{l-1}(\epsilon) K_{l+1}(\epsilon) + I_l(\epsilon) K_l(\epsilon)] \rightarrow \frac{l}{\epsilon} \quad (13)$$

The singularity in the latter expression reflects presence of exactly l zero modes supported by the sites of sublattice B .




FIG. 3: Numerical ($\circ$) and analytical (solid lines) results for the distribution of scaled Wigner delay times for sublattice A , for $\epsilon = 1$, $N_B = 300$ and $N_A = 300 - l$, $l = 0, 1, 2, 3$.

After straightforward manipulations one can find that the distribution Eq.(9) is replaced by the following two formulas:

$$\mathcal{P}_l(\tau_A) = \frac{\epsilon}{\tau_A \sqrt{1 - \tau_A}} e^{-\epsilon \left(\frac{2}{\tau_A} - 1 \right)} \quad (14)$$

$$\times \left[(v_+^l + v_-^l) I_{l+1}(\epsilon) + (v_+^{l+1} + v_-^{l+1}) I_l(\epsilon) \right],$$

$$\mathcal{P}_l(\tau_B) = \frac{\epsilon}{\tau_B \sqrt{1 - \tau_B}} e^{-\epsilon \left(\frac{2}{\tau_B} - 1 \right)} \quad (15)$$

$$\times \left[(v_+^l + v_-^l) I_{l-1}(\epsilon) + (v_+^{l-1} + v_-^{l-1}) I_l(\epsilon) \right].$$

valid for the sublattices A and B , respectively. Here the parameters v_+, v_- satisfy the conditions: $v_+ v_- = 1$ and $\frac{1}{2}(v_+ + v_-) = \left(\frac{2}{\tau_{A(B)}} - 1 \right)$. Finally, performing in Eq.(14) the limiting procedure discussed above, we arrive at the distribution of the (scaled) Wigner delay time $\tilde{\tau}_W$ for the one-channel lead attached to a site belonging to the A -sublattice:

$$\mathcal{P}_l(\tilde{\tau}_W) = \frac{1}{l!} \frac{1}{\tilde{\tau}_W^{l+2}} e^{-\frac{1}{\tilde{\tau}_W A}} \quad (16)$$

which generalizes the expression Eq.(10). In Fig. (3) we present the distribution of the Wigner delay times calculated numerically for various values of l compared with this analytical result.

In fact, the time-delay distributions Eqs. (10) and (16) can be obtained in a more direct way. For this we notice that the expression Eq.(8) for the unitary scattering matrix $S_A(E)$ at real energies E can be written in an equivalent form:

$$S_A(E) = \frac{\det \left(E^2 - iEP_{j_A} - \hat{H}\hat{H}^\dagger \right)}{\det \left(E^2 + iEP_{j_A} - \hat{H}\hat{H}^\dagger \right)} \quad (17)$$

where we used the $N_A \times N_A$ projection matrix $P_{j_A} = |j_A\rangle\langle j_A|$. Calculating now the Wigner delay time as the energy derivative of the logarithm of the above equation, and setting $E = 0$ we arrive after straightforward manipulations to a simple formula:

$$\tau_W = 2 \langle j_A | \left(\hat{H} \hat{H}^\dagger \right)^{-1} | j_A \rangle = 2 \sum_{n=1}^{N_A} \frac{|u_n(j_A)|^2}{\lambda_n^2} \quad (18)$$

Comparison of this expression with Eq.(4) makes it clear that the Laplace transform $P(s)$ of the probability density for $\tau_W = \tau_W/2N_A$ can be obtained via the same manipulations as those leading to Eqs.(5) and (6). For the general case $0 \leq l = N_B - N_A \ll N_A, N_B$ we find:

$$P(s) = \left\langle \frac{\det(\hat{H} \hat{H}^\dagger)}{\det(s/N_A^2 + \hat{H} \hat{H}^\dagger)} \right\rangle_H = \frac{2}{l!} s^{\frac{l+1}{2}} K_{l+1}(2\sqrt{s})$$

which can be immediately inverted yielding the distribution Eq.(16).

It is easy to repeat the same manipulations for the lead attached to a site of the larger sublattice B and to find that Eq.(18) is replaced formally with

$$\tau_W = 2 \langle j_B | \left(\hat{H}^\dagger \hat{H} \right)^{-1} | j_B \rangle \quad (19)$$

This expression, however, does not make any sense beyond the case $l = 0$ of equivalent sublattices, since the corresponding $N_B \times N_B$ matrix $\hat{H}^\dagger \hat{H}$ is singular. We conclude therefore that the Wigner delay time at zero energy diverges for the sites belonging to the larger sublattice due to presence of zero modes.

In summary, we presented analytical as well as numerical results for the distribution of the local density of states for zero-dimensional chaotic system at the point of chiral symmetry $E = 0$, and further utilized it for studying statistics of the reflection coefficient and Wigner delay times. Apart from investigating a gradual breakdown of the chiral symmetry with increasing energy parameter E in ergodic systems, an interesting and challenging question is to study the LDOS fluctuations in chiral systems of higher dimensions. In particular, in disordered quantum wires the mean DOS is known to display a logarithmic singularity[2, 3]. It would be interesting to understand how that singularity affects the LDOS distribution, and how it is reflected in fluctuations of the related scattering characteristics.

YVF is grateful to LPTMS, Universite Paris-Sud for kind hospitality and financial support during initial stage of this work. Financial support by Brunel University VC grant (YVF) and by a grant from the German-Israeli Foundation for Scientific Research and Development (AO) is gratefully acknowledged.

- [1] P.W.Brouwer C.Mudry, B.D.Simons, and A.Altland *Phys. Rev. Lett.* **81** (1998) 862; *Nucl.Phys.B* **565** (2000) , 653;
- [2] P.W.Brouwer, C.Mudry and A. Furusaki *Phys.Rev.Lett.* **84** (2000), 2913; M. Titov, P.W.Brouwer, A. Furusaki and C.Mudry *Phys. Rev. B* **63** (2001) 235318
- [3] A.Altland and R.Merkel *Nucl.Phys. B* **607** (2001), 511
- [4] R.Gade *Nucl.Phys.B* **398** (1993), 499; A.Eilmes, R.A.Römer and M.Schreiber, *Eur.Phys. J.B* **1**, (1998) 29
- [5] A. Altland and B.D.Simons *J.Phys.A* **32** (1999) L353; *Nucl. Phys.B* **562** (1999) 445; A. Furusaki *Phys.Rev.Lett.* **82** (1999) 604
- [6] For a review and further references see: J.J.M. Verbaarschot and T.Wettig *Annu.Rev.Nucl.Part.Sci.* **50**(2000) 343
- [7] K. Takahashi and S. Iida *Phys. Rev. B* **63** (2001), 214201
- [8] S.N. Evangelou and D.E.Katsanos *J.Phys.A* **36** (2003), 3237
- [9] A.Altland and M.R.Zirnbauer *Phys.Rev.B* **55** (1997), 1142
- [10] J.J.M. Verbaarschot and I.Zahed *Phys.Rev.Lett.* **70** (1993), 3852; K. Slevin, T. Nagao *Phys.Rev.B* **50** (1994), 2380; P.J. Forrester *Nucl.Phys.B* **402** (1993), 709;
- [11] A.V.Andreev, B.D.Simons, N.Taniguchi *Nucl.Phys.B* **432** (1994) 487
- [12] A.D.Jackson, M.K. Sener, J.J.M. Verbaarschot *Phys.Lett. B* **387** (1996), 355; *Nucl.Phys.B* **479** (1996), 707; T.Guhr and T.Wettig *J.Math.Phys.* **37** (1996), 6395; *Nucl.Phys.B* **506** (1997), 589; R.A.Janik, M.A.Novak and I.Zahed *Phys.Lett. B* **392** (1997), 155; G. Akemann, P.H.Damgaard, U.Magnea and S.Nishigaki *Nucl.Phys.B* **487** (1997), 721
- [13] D.Dalmazi and J.J.M. Verbaarschot *Nucl.Phys.B* **592** (2001), 419; Y.V.Fyodorov *Nucl.Phys.B* **621** (2002), 643; Y.V.Fyodorov and E.Strahov *Nucl.Phys.B* **647** (2002), 581
- [14] D.A.Ivanov *J.Math.Phys.* **43** (2002), 126
- [15] Y.V.Fyodorov and G.Akemann *JETP Lett.* **77** (2003) 438; K.Splittorff and J.J.M. Verbaarschot *Phys.Rev.Lett.* **90**(2003),041601
- [16] C.W.J. Beenakker, *Phys.Rev.B* **50**, 15170 (1994); N.Taniguchi, V.N.Prigodin *Phys.Rev.B* **54**, 14305 (1995)
- [17] Y.V.Fyodorov, *JETP Letters* **78**, 250 (2003) [cond-mat/0304671]
- [18] Y.V. Fyodorov, H.-J. Sommers, *J. Math. Phys.* **38** (4), 1918 (1997); V.A.Gopar et al. *Phys.Rev.Lett.* **77**, 3005 (1996); P.W.Brouwer et al. *Phys.Rev.Lett.* **78**, 4737 (1997);
- [19] C.W.J. Beenakker, P.W.Brouwer, *Physica E* **9**, 463 (2001); S.A. Ramakrishna, N. Kumar, *Phys. Rev.B* **61**, 3163 (2000)
- [20] T.Kottos, M.Weiss, *Phys. Rev. Lett.* **89**, 056401 (2002); A. Ossipov et al. , *Phys.Rev. B* **61**, 11411 (2000) and *Europhys. Lett.* **62**, 719 (2003), T.Kottos, A. Ossipov and T. Geisel cond-mat/0307119
- [21] D.V.Savin, H.-J.Sommers *Phys. Rev. E* **68**, 036211 (2003)

* On leave from Petersburg Nuclear Physics Institute RAS, 188350 Gatchina, Leningrad reg., Russia